



## Elite Series Technical Data

Property	Imperial Unit	Metric Unit	Description
<b>Fiber Type</b>			100% Polyethylene
<b>Fiber Mass</b>	10800 denier	12000 d tex	6 ply MS PRO
	4500 denier	5000 d tex	8 ply TXT thatch
	Root Zone	Root Zone	Every other needle
<b>Tufted Pile Height *</b>	1.75 in	44.5 mm	
<b>Color (s)</b>			Blend
<b>Tufting Gauge **</b>	1/4		
<b>Primary Backing</b>	7.0 oz/yd <sup>2</sup>	237 g/m <sup>2</sup>	Stabilized dual layered woven polypropylene
<b>Secondary Backing</b>	10.0 oz/yd <sup>2</sup>	339 g/m <sup>2</sup>	DuraFlo
<b>Non Woven Scrim</b>	2.7 oz/yd <sup>2</sup>	91.5 g/m <sup>2</sup>	

Property	Imperial Unit	Metric Unit	Test Method
<b>Tufted Face Weight</b>	80.0 oz/yd <sup>2</sup>	2713 g/m <sup>2</sup>	ASTM D418
<b>Total Weight</b>	99.7 oz/yd <sup>2</sup>	3381 g/m <sup>2</sup>	ASTM D418
<b>Permeability</b>	>45 inches per hour		DIN 18-035, part 6
<b>Tuft Bind</b>	6 lb - f	26 n	ASTM D1335
<b>Grab Tear MD</b>	200 lbs	91 kg	ASTM D5034
<b>Grab Tear CMD</b>	200 lbs	91 kg	ASTM D5034
<b>Infill Amount, recommend</b>			3-4 lb/ft <sup>2</sup>

Property	Imperial Unit	Metric Unit	Description
<b>Item Number</b>			Fescue Premier
<b>Tufted Roll Width</b>	15 ft.	4.57 m	

Robertson Industries is not responsible for typing errors.



TENCATE  
**Monoslide™ Pro**