

ABIC TESTING LABORATORIES, INC.

24 Spielman Road
Fairfield, NJ 07004

973-227-7060
Fax: 973-227-0172

To: TotTurf
Mr. Steve Scaturro

November 5, 2010

From: Leonard Mackowiak

Subject: Tear Strength
Project No 5398-02

Introduction

ABIC Testing Laboratories, Inc. was authorized to test the following samples for tear strength according to ASTM D-624. Testing was conducted on the material as received.

- TotTurf TPV
- TotTurf Aromatic
- TotTurf Supreme

Results:

<u>Test Product</u>	<u>Tear Strength (lbs)* ASTM D-624</u>	<u>Average (lbs)</u>
TotTurf TPV	9.8, 11.6, 11.4, 12.0, 12.0	11.4
TotTurf Aromatic	10.0, 8.8, 7.5, 8.4, 10.5	9.0
TotTurf Supreme	12.4, 15.0, 10.4, 12.4, 13.0	12.6

*** Samples cut using ASTM Die C**

Discussion

In our testing program the TotTurf Supreme produced the highest tear strength values by the test method using Die C cut samples.

Respectfully submitted,



Leonard Mackowiak
Vice President